

TECHNICAL INFORMATION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO

ROJO II

Polyurethane Minium Type Red Primer

506-09000-351



DESCRIPTION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO ROJO II, is primer formulated on polyurethane resins, so it has excellent chemical and abrasion resistance, and fast drying. Besides, it has antirust pigments that, by chemical action, prevent rust appearance. Easy to apply, good wetting properties, high adhesion and hi solids content. It has no toxics metals.

USE

This product can be applied on iron and carbon steel surfaces on indoors or outdoors of moderate aggressive environments. Once dry, it should be coated within 22 days with an alkyd or acrylic finish suitable to the surface.

Structure	Structural elements (columns, trusses, etc.), Metallic structure, aerial piping, gates, meshes, fences and gates.
Exterior/Interior	Outdoor, Roofed Outdoors, Indoor.
Surface	Carbon steel, iron.

CHARACTERISTICS

SPECIAL PROPERTIES

Finish	MATTE
Hiding Power	

PHYSICAL PROPERTY

DATA

Weight Solids (%)	75 - 77
Weight per gallon (kg/gal)	5.30 - 5.50
Volume solids (%)	56 - 58

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.

TECHNICAL INFORMATION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO

ROJO II

Polyurethane Minium Type Red Primer

506-09000-351



Stormer Krebs Viscosity (Ku)	90 - 95
Theoretical yield (m ² /gallon)	57m ² @ 1.5mils
VOC (volatile organic compounds) g/Lt.	<330

Definition of theoretical yield: Maximum surface that a paint can cover under ideal conditions. Practical performance varies depending on type of surface, used tool, applicator experience and other factors. 1 mil = 0.0254 mm.

Note: values expressed in a 1 to 5 scale, where 5 is better.

PRESENTATIONS

AVAILABLE CONTAINERS

¼ gallon metal can (0.946 lt)
1 gallon metal can (3.785 lt)
5 gallon plastic bucket (18.925 lt)

AVAILABLE COLORS

Rojo Óxido (Oxide red)

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.

TECHNICAL INFORMATION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO

ROJO II

Polyurethane Minium Type Red Primer

506-09000-351



SURFACE PREPARATION

CONDITION	INSTRUCTION
Surface Cleaning	<p>Before applying, remove any dirt, such as dust, grease, or other contaminants, as they can affect the adhesion or performance of the finish.</p> <p>Remove loose or peeling old paint film with the appropriate tools, and smooth uneven spots left by old coat of paint.</p>
New Iron	<p>Wash and degrease the surface, allow to dry completely and then apply a coat of this CORROSTOP TIPO MINIO ROJO II 9000-351 anticorrosive primer.</p> <p>Finally, coat with a SUR finish appropriate for this surface.</p>
Rust Galvanized Steel	<p>Rust spots should be cleaned with a steel brush or sandpaper to remove it. Remove residual dust (do not use water).</p> <p>In areas that cannot be adequately prepared due to their difficult access, apply a layer of CORROSTOP CONVERTIDOR DE ÓXIDO 375-013 (rust converter) patching it (only on rust spots).</p> <p>Allow it to act for 4 hours and then apply a coat of CORROSTOP TIPO MINIO ROJO II 9000-351 anticorrosive primer.</p> <p>Finally, coat with a SUR finish appropriate for this surface.</p>

PRODUCT PREPARATION

COMPONENT	MIXING RATIO	MIXING INSTRUCTIONS
Product: 506-09000-351, CORROSTOP TIPO MINIO ROJO II	100%	Stir well before use.
Diluent: 510-00456-900 DILUYENTE	10 to 15%	

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.

TECHNICAL INFORMATION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO

ROJO II

Polyurethane Minium Type Red Primer

506-09000-351



PRODUCT APPLICATION

IT CAN BE APPLIED WITH

Brush

Roller

Airless Equipment

Brushing

Use natural or synthetic brushes in good condition and that do not shed bristles.

Roller application

Microfiber or splatter free roller felt.

Smooth Surface: 3/8 "or 1/2" felt.

Rough surface: 3/4" felt

Airless Application

Nozzle	#517
--------	------

Pressure	1500 psi
----------	----------

Application conditions

Do not apply on hot surfaces or directly exposed to sunrays, paint will evaporate too soon and this will affect leveling, adhesion and durability.

Don't paint when humidity is over 85%, or in a rainy day.

Number of layers and thickness

Dry Coat Thickness	1.5 mils
--------------------	----------

Number of Coats	1
-----------------	---

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.

TECHNICAL INFORMATION

CORROSTOP PRIMARIO DE POLIURETANO TIPO MINIO

ROJO II

Polyurethane Minium Type Red Primer

506-09000-351



Drying times

Dry-to-Touch Time	4 – 5 hours
Re-coat time	12 hours

Drying times listed are under ideal conditions (Between 22–28°C temperature and 50 – 80% relative humidity). These times are dependent on temperature, moisture, film thickness and dilution.

OBSERVATIONS

- ✓ Keep container tightly closed in a ventilated place, between 20 and 30°C, out of reach of children.
- ✓ If you´ll use more than one container, mix them in advance to correct any color differences.
- ✓ Do not wash a painted surface with abrasive detergents, it is better to use liquid detergent with enough water and a soft sponge.
- ✓ If you need more information, check our website <https://www.gruposur.com/asistencia/>

HEALTH

- ✓ User may need to wear the appropriate Personal Protective Equipment, which is detailed in the respective Safety Data Sheet (MSDS), available at <http://www.gruposur.com>

If you need to dispose of empty containers of our products in Costa Rica, contact your SUR Color paint store or our industrial compound in La Uruca, San Jose.

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.