TECHNICAL INFORMATION

KIT TÉMPERA

522-00255-000



DESCRIPTION

TÉMPERA ARTISUR is an acrylic, water-based paint made with excellent quality pigments. Easy handling and easy to apply, its colors are innocuous and lead-free.

USE

It's a special paint for school use, but it has multiple uses. It can be applied on paper, cardboard, canvas and wood.

Superficie	Canvas, Wood, Bond Paper, Cardboard, MDF		
Line	Artistic Line, Domestic Line		

CARACTERÍSTICAS

SPECIAL PROPERTIES

Finish	Matte
Long-lasting	
Excellent quality	
Fast drying	
Easy to apply	
Ready to use	
Lead and mercury free	

PHYSICAL PROPERTIES	DATA
Weight per gallon (kg/gal)	4.40-4.60
Stormer Krebs Viscosity (Ku)	110 – 120
VOCs (grams/liter)	< 2.5
Weight solids (%)	33 – 35
Volume Solids (%)	18 - 20
рН	7 – 9
Shelf life	4 years

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.













TECHNICAL INFORMATION

KIT TÉMPERA

522-00255-000



00	N 17	- A I			2
CO	NI	A	IN	ы	K5

AVAILABLE CONTAINERS AVAILABLE COLORS

Kit with six colors, 1 Fl. Oz. (30 ml.) each Chart Colors

1 liter plastic bottle (1.06 qt.)

1 gallon plastic bottle (3.785 Lt.)

SURFACE PREPARATION

CONDITION INST

Surface preparation Surface should be dry and free of grease, oil, dust, or any other

contaminants.

PRODUCT PREPARATION

COMPONENT	MIXING RATIO	MIXING INSTRUCTIONS
Product: 522-00255-000, KIT TÉMPERA	100%	Stir well before use
Diluent: Tap water	10%	It can be diluted with 10% tap water

It can be applied with fingers, paintbrush or sponge, only over paper or cardboard.

PRODUCT APPLICATION

APPLICATION TOOL

Brush Finger Sponge Paintbrush

APPLICATION CONDITIONS

This product is designed for children to apply directly on paper or cardboard, using their fingers, brush, sponge or paintbrush.

This product should not be applied directly exposed to sunrays, rain, fog, or strong winds.

DRYING TIMES

Full drying time 15 minutes (depending on film thickness)

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.













TECHNICAL INFORMATION

KIT TÉMPERA

522-00255-000



APPLICATION INSTRUCTIONS

Washable with soap and water. To avoid permanent stains, wash clothing that has been in contact with the product as soon as possible.

NOTICE

- ✓ If you need more information, check our website https://www.gruposur.com/asistencia/
- Container must be kept out of reach of children, tightly closed in a ventilated place, away from sunlight or intense heat, between 20 and 30°C to avoid loss of its properties.

HEALTH

- ✓ The user of this product may need the appropriate Personal Protection Equipment (PPE), as described in its Safety data Sheet (MSDS), available at http://www.gruposur.com
- ✓ If you need to dispose of empty containers of our products in Costa Rica, contact your SUR store or our industrial compound in La Uruca, San Jose

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.









