

TECHNICAL INFORMATION

PINTURA VITRAL

Stained Glass Paint

522-22040-000



DESCRIPTION

Pintura Vitral is a paint specially designed to be applied on glass, so it has excellent transparency and leveling power. Formulated with solvent-based synthetic resins of excellent quality.

USE

This product is for indoor use only, to paint on glass surfaces, (glasses, cups, etc.) that won't be in contact with food. Colors can be mixed together.

Indoor/Outdoor Indoor

Surface Vidrio Glass

Line Artistic Line, Domestic Line

PROPERTIES

SPECIAL PROPERTIES

Good color intensity

Excellent quality

Easy to apply

Ready to use

High transparency

PHYSICAL PROPERTIES

DATA

Weight solids (%)	55 - 57
Weight per gallon (kg/gal)	4.0 - 4.2
Stormer Krebs Viscosity (Ku)	60 - 70
Volume Solids (%)	42 - 44

CONTAINERS

AVAILABLE CONTAINERS

1 Fl. Oz. (0.030 Lt.) glass bottle

COLOR(ES) DISPONIBLE(S)

Available in chart colors

SURFACE PREPARATION

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



Versión 2.0 del: Sep 9/15/2021
15 2021 5:29PM



TECHNICAL INFORMATION

PINTURA VITRAL

Stained Glass Paint

522-22040-000



CONDITION	INSTRUCTION
Surface preparation	Use alcohol to properly clean the glass surface before applying

PRODUCT PREPARATION

COMPONENT	MIXING RATIO	MIXING INSTRUCTIONS
Product: 522-22040-000, PINTURA VITRAL	100%	Ready to use, do not dilute. Do not stir before use.

PRODUCT APPLICATION

APPLICATION TOOL

Dropper Wooden stick

DRYING TIMES

Full drying time | 12 hours

Application instructions

Place the design under the glass and fix it.

The glass should be horizontal, as this is a self-leveling paint.

Outline each color with our Delineador para Vitral, code 522-22045-702 leading paste and let dry for 1 hour.

Apply this Pintura Vitral with a dripping technique, using a wooden toothpick or dropper.

Do not shake this product, since it can form bubbles.

If bubbles do appear, let stand still until bubbles disappear.

If, when applying the paint, bubbles appear, burst it with a needle.

NOTICE

- ✓ Only for indoor use
- ✓ Container must be kept out of reach of children, tightly closed in a ventilated place, away from sunlight or intense heat, between 20 and 30°C to avoid loss of its properties.

HEALTH

- ✓ Avoid contact with skin and eyes.

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



Versión 2.0 del: Sep 9/15/2021
15 2021 5:29PM



TECHNICAL INFORMATION

PINTURA VITRAL

Stained Glass Paint

522-22040-000



-
- ✓ The user of this product may need the appropriate Personal Protection Equipment (PPE), as described in its Safety data Sheet (MSDS), available at <http://www.gruposur.com>
 - ✓ If you need to dispose of empty containers of our products in Costa Rica, contact your SUR store or our industrial compound in La Uruca, San Jose

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



Versión 2.0 del: Sep 9/15/2021
15 2021 5:29PM

