

TECHNICAL INFORMATION

PEGAFORTE INDUSTRIAL ADHESIVE 161



525-23161-000

DESCRIPTION

PEGAFORTE Industrial Adhesive 161 offers excellent adhesion for low density softwood industry. It has regulated penetration, as well as quick drying. Due to its composition, it has a greater resistance to rehydration, so that it can withstand high humidity conditions without risk of adhesion failures.

USE

Pegaforte Industrial Adhesive 23161 was developed specifically for cigar boxes and similar manufactures.

Product line Professional/industrial Line

CHARACTERISTICS

ASSESSMENT

Finish Milky liquid

PHYSICAL PROPERTY

DATA

Volume Solids (%)	49 - 51
Weight solids (%)	53 - 55
Weight per Gallon (kg/Gl)	4.0 - 4.2
Brookfield Viscosity RFV (cPs)	2,500 - 3,500
Density (kg / l)	1.05 - 1.10
Maximum Wood moisture %	15%
pH	1 - 5

PRESENTATION

AVAILABLE PRESENTATIONS

5 Gallon plastic bucket (18.925 lt)

PRODUCT PREPARATION

COMPONENT	MIXING RATIO	MIXING INSTRUCTIONS
-----------	--------------	---------------------

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation or compatibility of products used; therefore, can only guarantee this product's quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission or inaccuracy in it.

TECHNICAL INFORMATION

PEGAFORTE INDUSTRIAL ADHESIVE 161



525-23161-000

Product: 525-23161-000 - PEGAFORTE
INDUSTRIAL ADHESIVE 161

100%

Ready to use. Do not dilute.

PRODUCT APPLICATION

IT CAN BE APPLIED WITH



Brush



Roller

Tools

Once parts are ready to be bonded, apply it with brush, roller, or similar equipment.

Application conditions

This product's performance depends on it being stored in indicate conditions.

Drying times

Due to variable film thickness, drying times are dependent on environment and application conditions.

OBSERVATIONS

- ✓ If you need more information, one of our technicians will assist you. Call 800-SUR-2000 or email us at customerservice@gruposur.com
- ✓ Store the product in its closed, sealed original container between 20°C and 30°C in a dry and ventilated place, far from sunlight, out of the reach of children.
- ✓ In low temperatures or high humidity environment, you can get longer drying times.
- ✓ Manage your inventory, you shouldn't use product stored for more than 6 months.
- ✓ If adhesive remains static for a long time, stir it before use.
- ✓ After expiration date, there is no guarantee that the product will retain its properties.
- ✓ Changes in environmental conditions can significantly affect open time and drying characteristics.

HEALTH

- ✓ Application personnel should use appropriate personal protective equipment, as detailed in its safety data sheet (MSDS), available at www.gruposur.com
- ✓ If you need to dispose of empty containers of our products in Costa Rica, contact your SUR Color paint store or our industrial compound in La Uruca, San Jose.

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation or compatibility of products used; therefore, can only guarantee this product's quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission or inaccuracy in it.