INFORMACIÓN TÉCNICA

FRAGUA PARA PISCINA MPI 660

Swimming Pool Grout

535-39660-001



DESCRIPTION

FRAGUA PARA PISCINAS MPI 660 is a grouting tile pool mortar, so it's resistant to constant immersion, designed for filling joints in swimming pool tiling. It can stand chemical attack of chlorine present in swimming pool water.

USE

Use only to grout spacings in swimming pool tiles, such as glass-ceramic, quarry or similar.

Structure	Pool	
Interior/Exterior	Outdoor, Indoor	
Surface	Concrete	
Line	Domestic Line	

PROPERTIES

SPECIAL PROPERTIES

Appearance	Old
	White,
	Grey,
	and
	Silver
	Grey

PHYSICAL PROPERTIES	DATA

CONTAINERS and COLORS				
AVAILABLE CONTAINERS	AVAILABLE COLORS			
2kg plastic bag	Old White, Grey, and Silver Grey			
SURFACE PREPARATION				
CONDITION	INSTRUCTION			
Grout	Surface to be applied must be dry, clean, solid, sound, free of mortar			

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.











INFORMACIÓN TÉCNICA

FRAGUA PARA PISCINA MPI 660

Swimming Pool Grout





residue in grout lines.

It should be free of water leaks, nor have it been treated with any waterproofing agent or paint.

PRODUCT PREPARATI	ON		
COMPONENT		MIXING RATIO	MIXING INSTRUCTION
Product: 535–3966 PISCINA MPI 660	0-001, FRAGUA PAF	RA 2kg	Stir well this product and then add water in the recommended quantity.
Diluent: CLEAN WATE	R	750ml	
PRODUCT APPLICATION TOOL	ON		
Putty knife	Smooth trowel	Rubber trowel	

Application conditions

This product should not be applied directly exposed to sunrays, rain, fog, or strong winds.

Pool tile should be well adhered

Surface Temperature	5°C − 35°C
DRYING TIMES	
Full cure	7 days

Instrucciones de aplicación

Mix by hand the entire bag content (2 kg) with 750 ml of clean water (3/4 litre) in a clean container until a uniform, lump-free mixture is obtained.

Let stand for 5 minutes and then apply with a rubber trowel on grout lines, filling all the tile gaps evenly.

Let dry for an hour and wipe off excess with a dry, semi-hard sponge.

If any void were left after the first application, refill the empty spots and repeat the procedure.

Initial curing time: 24 hours.

Do not use the product if it has already begun to harden (initial set).

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.













INFORMACIÓN TÉCNICA

FRAGUA PARA PISCINA MPI 660

Swimming Pool Grout

535-39660-001



Equipment cleaning

To clean tools use clean water

NOTICE

- ✓ Do not apply on hot surfaces or directly exposed to sunrays, as it will evaporate too soon, compromising leveling, adhesion and durability.
- Container must be kept out of reach of children, tightly closed in a ventilated place, away from sunlight or intense heat.
- ✓ If you need more information, check our website https://www.gruposur.com/asistencia/

HEALTH

- ✓ The user of this product may need the appropriate Personal Protection Equipment (PPE), as described in its Safety data Sheet (MSDS), available at http://www.gruposur.com
- ✓ If you need to dispose of empty containers of our products in Costa Rica, contact your SUR store or our industrial compound in La Uruca, San Jose.

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.









