

DESCRIPTION

KORAL DECO FINISH TWINKLE is a decorative wall coating creates a fabric-like texture, achieving an atmosphere full of movement and color.

USE

This product is for indoor use only. It can be applied on concrete, plasterboard, or wood surfaces.

Structure	Ceilings, walls
Interior/Exterior	Indoor
Surface	Concrete, Fiber cement, Wood, Gypsum

FEATURES

ASSESSMENT

Finish Glossy

PHYSICAL PROPERTIES

DATA

Weight solids (%)	26 - 28
Weight per gallon (kg/gal)	4.2 - 4.4
Volume solids (%)	24 - 26
Stormer Krebs Viscosity (cPs)	120 - 130
Theoretical yield (m ² /gallon)	37.5m ² @ 1 mil

Definition of theoretical yield: Maximum surface that a paint can cover in ideal conditions. Practical yield varies depending on type of surface, tool used, applicator experience and other factors. 1 mil = 0.0254 mm.

PRESENTATION

AVAILABLE CONTAINERS

¼ gallon (0.946 Lt.)
1 gal. can (3.785 Lt)

AVAILABLE COLORS

Gray 811
Orange 820
Pink 828
Violet 847

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.

Light Blue 858

SURFACE PREPARATION	
CONDITION	INSTRUCTION
Moisture Problems	Do not apply to surfaces that have or had moisture problems
Surface cleaning	Before applying, remove any dirt, such as dust, grease, or other contaminants, as this will affect the adhesion or performance of the finish. Remove badly adhered paint with the appropriate tools, and smooth out any irregularities (steps) left by old coats of paints.
Concrete	All new surfaces must fully be cured, usually about 30 days (setting time). Apply 1 coat of Sellador Blanco 522-000 (White Sealer) and let dry. Finally apply this coating.
Gypsum	Plaster the surface, sand and thoroughly clean residual dust with a moist microfiber cloth. Apply 1 coat of Sellador Blanco 522-000 (White Sealer) (diluted with 20 to 25% water to improve surface infiltration and let dry.
Drywall and fibercement	Dust thoroughly and apply a coat of Sellador Blanco (White Sealer) 522-000. Finally apply this coating.
Wood	Patch all holes and imperfections with Masilla para madera 800-*** (wood putty), sand and then apply one coat of Sellador Aparejo Universal (wood bonding primer) 00530-000. Finally apply this coating.
Mold, Mildew,	Apply Solución Antihongos 334-900 (Antifungal Solution), let on the surface for some 20 minutes. Rinse with enough clean water and scrub the area. Where washing is not possible, apply NIT CLINICAL DESINFECTANT CLEANER 4 33260-600 , scrub with a microfiber cloth, apply again and let dry on the surface. After cleaning, let dry completely before applying a coat of Sellador (sealer) 522-000 . Finally apply this coating.
Microcracks, fissures or cracks, in masonry or concrete	Hairline cracks (0.1 mm to 0.5 mm): an elastomeric finish is advised. Small Cracks (0.6 mm to 2 mm): Repair with Elastomeric Putty PEGA PATCH 231-000 . Cracks (2 mm a 20 mm): USE 550 ETIBOND CONCRET and immediately, "fresh on fresh", apply Mortero de Reparación MR-520 (repair mortar). Let the mortar cure and dry for at least 15 days before applying the finish. Once cracks repaired, use a coat of Sellador 522-000 (sealer) and this finish. Important: For cracks wider than described, refer to the Virtual Assistant or request an assessment from our Technical Service.

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



Mild concrete dusting	Apply a coat of SELLADOR TRANSPARENTE 501-910 (Clear Sealer), let dry and paint. Note: Evaluate dusting problem to determine if the surface can be painted or further reparation is required.
Glossy/satin surfaces	Apply Sellador Universal 524-000 (Universal Sealer) to ensure adhesion of any type of paint. Finally apply this finish.

PRODUCT PREPARATION

COMPONENT	MIXING RATIO	MIXING INSTRUCTIONS
Product: 596-48605-900, DECO FINISH CANVA	Ready for use, do not dilute.	Stir well before use

PRODUCT APPLICATION

Apply with:

Square decorative
Brush
Roller with higher
nap

TOOLS

1. Bicolor Roller felt D40 9" x 3/4" code R6500017580.
2. Rubber decorative Brush 12 x 12 code R6500007399.

Application Conditions

Do not apply when humidity is over 85%, when is raining or under direct rain threat.

Coats and thickness

Number of coats	Minimum 2
-----------------	-----------

Dying Times

Time to recoat	3 hours
----------------	---------

Drying times listed are under ideal conditions (Between 22-28°C temperature and 50 - 80% relative humidity). These times are dependent on temperature, moisture, film thickness and dilution.

Application Instructions

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



INFORMACIÓN TÉCNICA

DECO FINISH CANVA

596-48605-900



1. Shake the container.
2. Pour the product into a paint tray.
3. Submerge the roller felt in the tray, to be sure all the nap is embedded on the product.
4. Apply it on the wall, just as any regular paint and, while the coating is still wet, slide the decorative Square Brush in vertical long strokes.
5. Let dry for three hours and apply a second coat in a similar way but, this time around, slide the Decorative Brush horizontally.
6. Approximate practical yield: 8m² per gallon.

Notes

For more information on special effects with this product, ask our Technical Service Department.

REMARKS

- ✓ Keep container tightly closed in a ventilated place, between 20 and 30 °C, out of reach of children. If you'll use more than one container, mix them in advance to correct any color differences. Do not wash a painted surface with abrasive detergents, it is better to use liquid detergent with enough water and a soft sponge. If you need more information, check our website <https://www.gruposur.com/asistencia/>

HEALTH

- ✓ If you need to dispose of empty containers of our products in Costa Rica, contact your SUR Color paint store or our industrial compound in La Uruca, San Jose.

The user of this product may need the appropriate Personal Protection Equipment (PPE), as described in its Safety data Sheet (MSDS), available at <http://www.gruposur.com>

These technical data were calculated under controlled laboratory conditions, but SUR QUIMICA has no control over conditions, tools, applicator skills, selection, preparation, or compatibility of products used; therefore, can only guarantee this product quality, its features and qualities' suitability, but is not responsible for the results obtained in conditions impossible to check once the job has been done. SUR QUIMICA has made reasonable efforts to ensure the accuracy of the information provided here, but assumes no responsibility for any error, omission, or inaccuracy in it. If there is any inconsistency between different language issues of this document, Spanish version will prevail.



Versión 3.0 del: Jul 7/15/2019
15 2019 8:35AM

